



# PTT LI-PLEX GREASE

## Mỡ Lithium Complex

### Tổng quan

- PTT Li-Plex Grease NLGI 2, 3: là mỡ chất lượng cao, sản xuất từ bột lithium, phụ gia chống rỉ, chống mài mòn và chống ô xi hóa

### Ưu điểm

- Bền nhiệt và ô xi hóa
- Bảo vệ chống rỉ và mài mòn rất tốt
- Điểm rơi cao giúp giảm tránh chảy ở nhiệt độ cao
- Ngăn bụi bẩn tiếp xúc với các bộ phận chuyển động
- Chống mài mòn ở tải trọng cao

### Ứng dụng

- Khuyến cáo sử dụng trong ô tô và các ứng dụng công nghiệp nặng như vòng bi, trục bi với nhiệt độ hoạt động bình thường ở 150°C

### Tiêu chuẩn

NLGI

### Thông số tham khảo

	<b>NLGI 2</b>	<b>NLGI 3</b>
Loại	Lithium	Lithium
Độ xuyên kim ở 25°C, 1/10 mm	269	236
Điểm rơi, °C	356	358
4-Ball Wear, mm	0.46	0.49
4-Ball EP		
- Weld Load, Kg <sub>f</sub>	315	315
- Load Wear Index, Kg <sub>f</sub>	49.65	51.12
Màu	Xanh	Xanh

CÔNG TY CỔ PHẦN KHO VẬN VÀ DỊCH VỤ THƯƠNG MẠI (VINATRANCO)

Nhà phân phối dầu mỡ nhờ ủy quyền của tập đoàn PTT (Thái Lan)

Địa chỉ : 473 Minh Khai – Hai Bà Trưng – Hà Nội

Điện thoại : (+84-4)-3862 3566/Fax: (+84-4)-3862 1214 – Email : info@vinatranco.vn

Website : vinatranco.com.vn



# PTT LI-PLEX GREASE

## Lithium Complex Grease

### Descriptions

- PTT Li-Plex Grease NLGI 2, 3 : are high quality greases, produced from Lithium complex soap, anti-rust, anti-corrosion and anti-oxidant additives.

### Special Properties

- Good thermal and oxidation stability
- Provide superb rust and corrosion protection
- High dropping point minimize leakage at elevated temperatures
- Prevent dust and dirt from reaching into the moving parts
- Against wear under high load

### Applications

- Recommend for using in heavy duty motor vehicles and industrial applications such as wheel bearings, rolling bearings with normal operating temperature up to 150 °C

### Reference Standards

- NLGI

### Typical Values

	NLGI 2	NLGI 3
Soap Type	Lithium Complex	Lithium Complex
Penetration at 25 °C (Worked), 1/10 mm	269	236
Dropping Point, °C	356	358
4-Ball Wear, mm	0.46	0.49
4-Ball EP		
- Weld Load, kg <sub>f</sub>	315	315
- Load Wear Index	49.65	51.12
Timken OK Load, lb	45	45
Color	Blue	Blue

For more information, please contact Lubricants Technical Services Division, PTT Public Company Limited : Tel. (662) 239-7908, (662) 239-7987 Fax.

(662) 239-7858 Lube Hot Line (662) 239-7878